



GLAZIER INTERNATIONAL FZC

PO Box 42326, Sharjah, Tel : +971504833176 / +971552313669, Email : info@glazierinternational.com
TRN No : 100339496000003

FERRO SILICON BARIUM

Specification	Ba	Si	Al	Ca	C	Mn	S
Ba 2-3	2-3% min	68-73% min	1-2% max	1-2% max			
Ba 4-6	4-6% min	68-72% min	1-2% max	1-2% max			
Ba 6-8	6-8% min	65-70% min	1-2% max	1-2% max			
Ba 10	10% min	60-70% min	2.0% max	2.0% max	1.0% max		0.05% max
Ba 20	20% min	55% min	2.0% max	3.0% max	1.0% max	0.4% max	0.05% max
Ba 25	25% min	55% min	2.0% max	3.0% max	1.0% max	0.4% max	0.05% max
Ba 30	30% min	50% min	2.0% max	3.0% max	1.0% max	0.4% max	0.05% max
Ba 35	35% min	45% min	2.0% max	3.0% max	1.0% max	0.4% max	0.08% max



Packing : 1 ton Jumbo Bags unless otherwise specified.

Certificate of Conformity : Will be issued by Glazier if you need a third party Analysis it will be issued at the buyer's cost.