



# GLAZIER INTERNATIONAL FZC

PO Box 42326, Sharjah, Tel : +971504833176 / +971552313669, Email : [info@glazierinternational.com](mailto:info@glazierinternational.com)

TRN No : 100339496000003

## NEUTRAL RAMMING MASS

**PRODUCT NAME: NORVIBE™ A 1251 R**

TYPICAL PHYSICAL PROPERTIES		
PROPERTIES	UNIT	TYPICAL VALUES
GRAIN SIZE	mm	6.30
DRIED DENSITY (RAMMED)	(gm/cc)	2.81
INITIAL SINTERING TEMPERATURE	(°C)	1300
FINAL SINTERING TEMPERATURE	(°C)	1750
MAX USE TEMPERATURE	(°C)	1800
STORAGE	Store in a cool and dry place	
LIMIT OF STORAGE	9 Months	
PACKING	Packed in 25 kg Polypropylene valve bags, on pallets in 1000 kg units	

CHEMICAL ANALYSIS		
%	Al <sub>2</sub> O <sub>3</sub>	MgO
	85.4	11.9

