



GLAZIER INTERNATIONAL FZC

PO Box 42326, Sharjah, Tel : +971504833176 / +971552313669, Email : info@glazierinternational.com
TRN No : 100339496000003

409 MODIFIED PUNCHINGS



Our Grade 409 Punchings are great for making low carbon stainless steel castings.

With a 12% chrome, a carbon Max of 0.01% and 0.80 % Ni, You get a low carbon Grade and don't have to add as much FeCr or FeNi to make your casting to specification.


Sizing is 150mm long x 50mm thick.



GLAZIER INTERNATIONAL FZC

PO Box 42326, Sharjah, Tel : +971504833176 / +971552313669, Email : info@glazierinternational.com
TRN No : 100339496000003

STAINLESS 304L



304L is available in plate form.

Sizing is 200mm plates and under x 10 – 50mm thick.

STAINLESS 304L TYPICAL CHEMICAL ANALYSIS

C - 0.02	Mn - 1.74	P - 0.02	S - 0.005
Si - 0.023	Ni - 8.09	Cr - 18.14	Mo - 0.363
Cu - 0.041	Al - 0.005	N - 0.08	V - 0.06

STAINLESS 304L SPEC CHEMICAL ANALYSIS


C - <0.03	Mn - 2.00 MAX	P - 0.045 MAX	S - 0.03 MAX
Si - 1.00 MAX	Ni - 8 - 12	Cr - 18 - 20	



GLAZIER INTERNATIONAL FZC

PO Box 42326, Sharjah, Tel : +971504833176 / +971552313669, Email : info@glazierinternational.com
TRN No : 100339496000003

STAINLESS 316L



316L is available in plate form.

Sizing is 200mm plates and under x 12 – 50mm thick.

STAINLESS 316L TYPICAL CHEMICAL ANALYSIS

C - 0.022	Mn - 1.57	P - 0.019	S - 0.005
Si - 0.322	Ni - 10.22	Cr - 16.15	Mo - 2.02
Cu - 0.459			

STAINLESS 316L SPEC CHEMICAL ANALYSIS

C - <0.03	Mn - 2.00 MAX	P - 0.045 MAX	S - 0.03 MAX
Si - 1.00 MAX	Ni - 10 - 14	Cr - 16 - 18	Mo - 2 - 3